



ProClean Degreaser™ Concentrate How-To Guide

Step 1: Preparation

- Cover areas at risk of over-spray with plastic drop cloth.
- Remove paint or previously applied sealer using Soy Gel Stripper.
- Remove carpet glue or other adhesives using Bean-E-Doo® Mastic Remover.

Step 2: Application

Coverage rate is approximately 200 square feet per gallon. Coverage rates may vary based on concrete texture, surface porosity, and application method.

NOTE: Only apply ProClean Degreaser™ when surface temperature is above 40°F (4°C).

Caution: May be harmful if swallowed or ingested. Contact with skin can cause mild irritation. Avoid contact with eyes.

Mixing:

- Mix Ratio: 4 ounces of ProClean Degreaser™ Concentrate to one gallon of water
- Remove all filters from pump-up sprayer.
- Pour ProClean Degreaser™ into pump-up sprayer.
- Pour water into sprayer.
- Tightly seal lid and shake vigorously for 20 seconds.
- Allow the ProClean Degreaser™ to sit for one minute before applying.

Spraying:

- Spray ProClean Degreaser™ on entire surface (let soak for 30 seconds).
- Clean surface with a scrub brush, cotton mop, or low-speed floor buffer with brush attachment.
- Pick up residue with a clean cotton mop or wet-dry vac.
- Immediately rinse surface with water until surface is clear of residue.
- Dry for at least eight hours before applying a stain or sealer.

Pro Tips:

- Break larger areas down into manageable zones (200-400 square feet), allowing enough time to finish cleaning surface before it dries.

Cleanup:

- Clean tools and supplies with ProClean Degreaser™ and warm water.



ProClean Degreaser™ Concentrate How-To Guide

Tools & Supplies:

- Pump-up sprayer
- Spiked shoes
- ProClean Degreaser™
- Scrub brush, cotton mop, or low-speed floor buffer with brush attachment
- Wet-dry vac or mop and bucket
- Plastic drop cloth

Disclaimer: Direct Colors does not warranty or guarantee results (outcomes). Concrete variations or improper application may cause unintended results. Test product on an inconspicuous or small area and allow to fully cure to ensure compatibility and desired result.